

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
15 November 2001 (15.11.2001)

PCT

(10) International Publication Number
WO 01/86727 A2

(51) International Patent Classification⁷: **H01L 29/24**

(21) International Application Number: PCT/US01/04957

(22) International Filing Date: 15 February 2001 (15.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/567,717 10 May 2000 (10.05.2000) US

(71) Applicant: **CREE, INC.** [US/US]; 4600 Silicon Drive,
Durham, NC 27703 (US).

(72) Inventors: **ALLEN, Scott, T.**; 1915 Misty Water Court,
Apex, NC 27502 (US). **PALMOUR, John, W.**; 2920
Hunter's Bluff Drive, Raleigh, NC 27606 (US). **AL-**
CORN, Terrence, S.; 309 Edgemore Avenue, Apex, NC
27502 (US).

(74) Agent: **MYERS, BIGEL, SIBLEY & SAJOVEC, P.A.**;
P.O. Box 37428, Raleigh, NC 27627 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— *without international search report and to be republished
upon receipt of that report*

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: SILICON CARBIDE METAL-SEMICONDUCTOR FIELD EFFECT TRANSISTORS AND METHODS OF FABRI-
CATING SILICON CARBIDE METAL-SEMICONDUCTOR FIELD EFFECT TRANSISTORS

(57) Abstract: SiC MESFETs are disclosed which utilize a semi-insulating SiC substrate which substantially free of deep-level dopants. Utilization of the semi-insulating substrate may reduce back-gating effects in the MESFETs. Also provided are SiC MESFETs with a two recess gate structure. MESFETs with a selectively doped p-type buffer layer are also provided. Utilization of such a buffer layer may reduce output conductance by a factor of 3 and produce a 3db increase in power gain over SiC MESFETs with conventional p-type buffer layers. A ground contact may also be provided to the p-type buffer layer and the p-type buffer layer may be made of two p-type layers with the layer formed on the substrate having a higher dopant concentration. SiC MESFETs according to embodiments of the present invention may also utilize chromium as a Schottky gate material. Furthermore, an oxide-nitride-oxide (ONO) passivation layer may be utilized to reduce surface effects in SiC MESFETs. Also, source and drain ohmic contacts may be formed directly on the n-type channel layer, thus, the n+ regions need not be fabricated and the steps associated with such fabrication may be eliminated from the fabrication process. Methods of fabricating such SiC MESFETs and gate structures for SiC FETs as well as passivation layers are also disclosed.

WO 01/86727 A2

SILICON CARBIDE METAL-SEMICONDUCTOR FIELD EFFECT
TRANSISTORS AND METHODS OF FABRICATING SILICON CARBIDE
METAL-SEMICONDUCTOR FIELD EFFECT TRANSISTORS

FIELD OF THE INVENTION

The present invention relates microelectronic devices and more particularly to metal-semiconductor field-effect transistors (MESFETs) formed in silicon carbide.

5

BACKGROUND OF THE INVENTION

Electrical circuits requiring high power handling capability (>20 watts) while operating at high frequencies such as radio frequencies (500 MHz), S-band (3 GHz) and X-band (10 GHz) have in recent years become more prevalent. Because of the increase in high power, high frequency circuits there has been a corresponding increase in demand for transistors which are capable of reliably operating at radio frequencies and above while still being capable of handling higher power loads. Previously, bipolar transistors and power metal-oxide semiconductor field effect transistors (MOSFETs) have been used for high power applications but the power handling capability of such devices may be limited at higher operating frequencies. Junction field-effect transistors (JFETs) were commonly used for high frequency applications but the power handling capability of previously known JFETs also may be limited.

Recently, metal-semiconductor field effect transistors (MESFETs) have been developed for high frequency applications. The MESFET construction may be preferable for high frequency applications because only majority carriers carry current. The MESFET design may be preferred over current MOSFET designs because the reduced gate capacitance permits faster switching times of the gate input. Therefore, although all field-effect transistors utilize only majority carriers to carry

current, the Schottky gate structure of the MESFET may make the MESFET more desirable for high frequency applications.

In addition to the type of structure--and perhaps more fundamentally--the characteristics of the semiconductor material from which a transistor is formed also affects the operating parameters. Of the characteristics which affect a transistor's operating parameters, the electron mobility, saturated electron drift velocity, electric breakdown field and thermal conductivity may have the greatest effect on a transistor's high frequency and high power characteristics.

Electron mobility is the measurement of how rapidly an electron is accelerated to its saturated velocity in the presence of an electric field. In the past, semiconductor materials which have a high electron mobility were preferred because more current could be developed with a lesser field, resulting in faster response times when a field is applied. Saturated electron drift velocity is the maximum velocity which an electron can obtain in the semiconductor material. Materials with higher saturated electron drift velocities are preferred for high frequency applications because the higher velocity translates to shorter times from source to drain.

Electric breakdown field is the field strength at which breakdown of the Schottky junction and the current through the gate of the device suddenly increases. A high electric breakdown field material is preferred for high power, high frequency transistors because larger electric fields generally can be supported by a given dimension of material. Larger electric fields allow for faster transients as the electrons can be accelerated more quickly by larger electric fields than by smaller.

Thermal conductivity is the ability of the semiconductor material to dissipate heat. In typical operations, all transistors generate heat. In turn, high power and high frequency transistors usually generate larger amounts of heat than small signal transistors. As the temperature of the semiconductor material increases, the junction leakage currents generally increase and the current through the field effect transistor generally decreases due to a decrease in carrier mobility with an increase in temperature. Therefore, if the heat is dissipated from the semiconductor, the material will remain at a lower temperature and be capable of carrying larger currents with lower leakage currents.

In the past, most high frequency MESFETs have been manufactured of n-type III-V compounds, such as gallium arsenide (GaAs) because of their high electron mobilities. Although these devices provided increased operating frequencies and

moderately increased power handling capability, the relatively low breakdown voltage and the lower thermal conductivity of these materials have limited their usefulness in high power applications.

5 Silicon carbide (SiC) has been known for many years to have excellent physical and electronic properties which should theoretically allow production of electronic devices that can operate at higher temperatures, higher power and higher frequency than devices produced from silicon (Si) or GaAs. The high electric breakdown field of about 4×10^6 V/cm, high saturated electron drift velocity of about 2.0×10^7 cm/sec and high thermal conductivity of about $4.9 \text{ W/cm}^\circ\text{K}$ indicate that
10 SiC would be suitable for high frequency, high power applications. Unfortunately, difficulty in manufacturing has limited the usefulness of SiC for high power and high frequency applications.

Recently, MESFETs having channel layers of silicon carbide have been produced on silicon substrates (see U.S. Pat. Nos. 4,762,806 to Suzuki et al and
15 4,757,028 to Kondoh et al). Because the semiconductor layers of a MESFET are epitaxial, the layer upon which each epitaxial layer is grown affects the characteristics of the device. Thus, a SiC epitaxial layer grown on a Si substrate generally has different electrical and thermal characteristics than a SiC epitaxial layer grown on a different substrate. Although the SiC on Si substrate devices described in U.S. Pat.
20 Nos. 4,762,806 and 4,757,028 may have exhibited improved thermal characteristics, the use of a Si substrate generally limits the ability of such devices to dissipate heat. Furthermore, the growth of SiC on Si generally results in defects in the epitaxial layers which result in high leakage current when the device is in operation.

Other MESFETs have been developed using SiC substrates. U.S. patent
25 application Ser. No. 07/540,488 filed Jun. 19, 1990 and now abandoned, the disclosure of which is incorporated entirely herein by reference, describes a SiC MESFET having epitaxial layers of SiC grown on a SiC substrate. These devices exhibited improved thermal characteristics over previous devices because of the improved crystal quality of the epitaxial layers grown on SiC substrates. However, to
30 obtain high power and high frequency it may be necessary to overcome the limitations of SiC's lower electron mobility.

Similarly, commonly assigned United States Patent No. 5,270,554 to co-inventor Palmour describes a SiC MESFET having source and drain contacts formed on n^+ regions of SiC and an optional lightly doped epitaxial layer between the

substrate and the n-type layer in which the channel is formed. United States Patent No. 5,925,895 to Sriram *et al.* also describes a SiC MESFET and a structure which is described as overcoming "surface effects" which may reduce the performance of the MESFET for high frequency operation. Sriram *et al.* also describes SiC MESFETs which use n^+ source and drain contact regions as well as a p-type buffer layer. However, despite the performance reported in these patents, further improvements may be made in SiC MESFETs.

SUMMARY OF THE INVENTION

Embodiments of the present invention may provide SiC MESFETs formed on a semi-insulating substrate of SiC where the SiC substrate is substantially free of deep level dopants. Forming SiC MESFETs on such semi-insulating substrates may improve performance by reducing back-gating effects which may result from the presence of deep level dopants in the substrate. Buffer layers of p-type, n-type or undoped SiC may be utilized with such semi-insulating SiC substrates in the formation of MESFETs according to embodiments of the present invention.

In additional embodiments of the present invention, a two recess gate structure may be utilized where a cap layer of n-type SiC is formed on an n-type SiC channel layer. A recess is formed in the cap layer and a second recess is formed in the n-type channel layer by forming the second recess in the recess in the cap layer. The Schottky gate contact may then be formed in the second recess.

Further embodiments of the present invention may be provided by SiC MESFETs which utilize a selectively doped p-type buffer layer, where the p-type buffer layer has a carrier concentration of from about 1×10^{16} to about $1 \times 10^{17} \text{ cm}^{-3}$ and more preferably from about 3 to about $5 \times 10^{16} \text{ cm}^{-3}$. Utilization of such a buffer layer has unexpectedly been found to reduce output conductance by a factor of 3 and produce a 3db increase in power gain over SiC MESFETs with conventional p-type buffer layers.

SiC MESFETs according to embodiments of the present invention may also utilize chromium as a Schottky gate material. Furthermore, an oxide-nitride-oxide (ONO) passivation layer may be utilized to reduce surface effects in SiC MESFETs. Also, source and drain ohmic contacts may be formed directly on the n-type channel layer, thus, the n^+ regions need not be fabricated and the steps associated with such fabrication may be eliminated from the fabrication process.

Additionally, if a p-type buffer layer is utilized, a contact may be formed to the p-type buffer layer so as to allow grounding of the p-type buffer layer. The contact may be formed on a p^+ well region formed in the p-type buffer layer.

Optionally, the p-type buffer layer may be formed by two p-type layers where the first
5 layer formed on the substrate has a higher doping level than the second layer which is formed on the first p-type layer.

Particular embodiments of the present invention may provide a high power, high frequency, metal-semiconductor field-effect transistor having a bulk single crystal silicon carbide substrate and an n-type epitaxial layer of n-type conductivity
10 silicon carbide on the substrate. A p-type epitaxial layer of selectively doped p-type conductivity silicon carbide is provided between the substrate and the n-type epitaxial layer. The transistor may also include ohmic contacts for defining a source and a drain as well as a Schottky metal contact.

In other embodiments of the present invention, a high power, high frequency,
15 metal-semiconductor field-effect transistor may be provided having an n-type layer of n-type conductivity silicon carbide on a silicon carbide substrate and a p-type layer of p-type conductivity silicon carbide between the substrate and the n-type layer. Ohmic contacts are provided on portions of the n-type layer and spaced apart which respectively define a source and a drain. A region of chromium is also provided on a
20 portion of the n-type layer that is between the ohmic contacts and thereby between the source and the drain so as to provide a Schottky metal contact for forming an active channel in the n-type layer between the source and the drain when a bias is applied to the Schottky metal contact.

In further embodiments of the present invention, an overlayer is formed on the
25 ohmic contacts and the Schottky metal contact. Preferably, the ohmic contacts are formed of nickel and the overlayer includes layers of titanium, platinum and gold.

Furthermore, the layers of the transistors according to the present invention may form a mesa having sidewalls extending downward from the n-type layer into the p-type layer which define the periphery of the transistors. Optionally, the sidewalls
30 of the mesa may extend downward into the substrate. A passivation layer may also be provided on the sidewalls of the mesa and exposed portions of the n-type epitaxial layer. Preferably, the passivation layer is an ONO passivation layer.

In still further embodiments of the present invention, the Schottky metal contact is recessed in the active channel portion of the n-type epitaxial layer. The

Schottky metal contact may also be a mushroom gate contact. The Schottky metal contact may also include an overlayer having layers of platinum and gold.

Metallization may also be formed on the substrate opposite the n-type layer. Preferably, the metallization includes layers of titanium, platinum and gold coated
5 with an overlayer of eutectic alloy of AuGe.

The substrate may also be semi-insulating silicon carbide. While in particular embodiments it is preferred to utilize a semi-insulating substrate which is substantially free of deep level dopants, in other embodiments a semi-insulating silicon carbide substrate may be silicon carbide with a deep level dopant incorporated
10 therein. The deep level dopant may be vanadium. Preferably, the semi-insulating substrate has a resistance of greater than about 10,000 Ω -cm.

In still further embodiments of the present invention, the ohmic contacts may be formed on regions of n^+ silicon carbide which may be formed in the n-type epitaxial layer by ion implantation or, alternatively, formed directly on the n-type
15 epitaxial layer.

Aspects of the present invention also may provide methods of fabricating a metal-semiconductor field-effect transistor by forming a p-type epitaxial layer of selectively doped p-type conductivity silicon carbide on a single crystal silicon carbide substrate, wherein the p-type conductivity silicon carbide has a carrier
20 concentration of from about 1×10^{16} to about $1 \times 10^{17} \text{ cm}^{-3}$, then forming an n-type epitaxial layer of n-type conductivity silicon carbide on the p-type epitaxial layer, then forming ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain and forming a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain.
25 The n-type epitaxial layer and the p-type epitaxial layer may be etched to form a mesa. Furthermore in a preferred embodiment, the formation of ohmic contacts and a Schottky gate contact are preceded by etching the n-type epitaxial layer and the p-type epitaxial layer to form a mesa and forming an ONO passivation layer on the exposed surfaces of the mesa.

In particular embodiments of the present invention, the ONO passivation layer is formed by high temperature annealing exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer in an H_2 ambient and then forming an SiO_2 layer on the exposed portions of the substrate, p-type epitaxial layer and n-type
30

epitaxial layer. The SiO_2 layer is then argon annealed and oxidized. A layer of Si_3N_4 is then deposited on the oxidized SiO_2 layer and oxidized to provide the ONO structure.

5 In particular embodiments of the present invention, the high temperature anneal is carried out at a temperature of greater than about 900°C for a time of from about 15 minutes to about 2 hours. Furthermore, the argon anneal may be carried out at a temperature of about 1200°C for a time of about 1 hour.

10 The SiO_2 layer may also be formed to a thickness of from about 50 to about 500 Å. Preferably, the SiO_2 layer is formed through a dry oxide process at a temperature of about 1200°C . Also, the SiO_2 layer is preferably oxidized in a wet environment at a temperature of about 950°C for a time of about 180 minutes.

15 The layer of Si_3N_4 may be deposited to a thickness of from about 200 to about 2000 Å. Preferably, the layer of Si_3N_4 is deposited through chemical vapor deposition such as PECVD or LPCVD. The Si_3N_4 layer is also preferably oxidized in a wet environment at a temperature of about 950°C for a time of about 180 minutes. The Si_3N_4 layer may be oxidized to provide an oxide layer having a thickness of from about 20 to about 200 Å.

20 In other embodiments of the present invention, a gate recess is formed in the n-type epitaxial layer and the Schottky gate contact formed in the gate recess. Preferably, the gate recess is formed by etching through the ONO passivation layer and into the n-type epitaxial layer so as to provide a gate recess in the n-type epitaxial layer and the Schottky gate contact formed in the gate recess utilizing the ONO passivation layer as a mask. Furthermore, the step of etching through the ONO passivation layer may be followed by patterning the ONO passivation layer so as to provide a ledge in sidewalls of the opening of the ONO passivation layer for the gate recess. A mushroom gate structure may then be formed in the gate recess and on the sidewalls and ledge of the ONO passivation layer. The etching of the ONO passivation layer may be carried out by Electron Cyclotron Resonance or Inductively Coupled Plasma etching.

30 In a still further embodiment of the present invention, n^+ well regions are implanted in the n-type epitaxial layer so as to provide source and drain regions and the ohmic contacts formed on the n^+ well regions.

In a still further aspect of the present invention, the substrate is thinned and a metallization layer formed on the substrate opposite the p-type epitaxial layer. The

metallization layer may be formed by forming a titanium layer on the substrate opposite the p-type epitaxial layer, then forming a layer of platinum on the titanium layer; and then forming a layer of gold on the layer of platinum. A layer of a eutectic alloy of AuGe may also be formed on the layer of gold.

5 In another aspect of the present invention methods of fabricating a gate structure for a silicon carbide field effect transistor is provided by forming an ONO passivation layer on exposed surfaces of a mesa terminated silicon carbide field effect transistor, forming a gate window in the ONO passivation layer, forming a gate recess in a channel layer of the mesa terminated silicon carbide transistor and forming a gate
10 contact in the gate recess in the channel layer. The ONO passivation layer is preferably formed as described above. Furthermore, the mushroom gate structure may also be formed as described above.

 In still further embodiments of the present invention, methods of fabricating a passivation layer of a silicon carbide semiconductor device are provided by forming
15 an oxide layer on the silicon carbide semiconductor device and then annealing the oxide layer in a NO environment. The oxide layer may be thermally grown or deposited. Furthermore, the anneal in the NO environment may be followed by depositing a layer of Si_3N_4 on the oxidized SiO_2 layer and then oxidizing the layer of Si_3N_4 .

20 In particular embodiments, the oxide layer may be formed by high temperature annealing exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer in an H_2 ambient and then forming an SiO_2 layer on the exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer, argon annealing the SiO_2 layer and oxidizing the SiO_2 layer.

25 In still further embodiments of the present invention, a double recessed gate MESFET may be fabricated by forming an n-type epitaxial layer of n-type conductivity silicon carbide on a silicon carbide substrate, forming ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain, forming a cap layer of n-type silicon carbide on the n-type epitaxial layer, forming a first recess in
30 the cap layer, forming a second recess in the n-type epitaxial layer, wherein the recess in the n-type epitaxial layer is within the first recess in the cap layer, and forming a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain to form an active channel in the n-type epitaxial layer between the source and the drain when a bias is applied to the

Schottky metal contact wherein the Schottky metal contact is within the recess in the n-type epitaxial layer.

In particular embodiments, the formation of an n-type epitaxial layer and a cap layer are provided by epitaxially growing the n-type epitaxial layer and the cap layer in a single growth step. Furthermore, in still further embodiments, an n-type dopant concentration in the single growth step may be changed to grow the cap layer.

In yet additional embodiments of the present invention, the first recess in the cap layer may be formed by patterning the cap layer to form the first recess. Furthermore, a mesa having sidewalls which extend through the cap layer and the n-type epitaxial layer may also be formed. In such embodiments, the patterning of the cap layer to form the first recess may be followed by forming an ONO passivation layer on exposed surfaces of the mesa and the first recess, forming a gate window in the ONO passivation layer, wherein the gate window is within the first recess, forming the second recess in n-type epitaxial layer and forming a gate contact in the second recess.

In still further embodiments, the substrate may be formed by forming a semi-insulating SiC substrate which is substantially free of deep-level dopants. Also, a buffer layer may be formed between the substrate and the n-type epitaxial layer. The buffer layer may be undoped SiC, n-type SiC or p-type SiC. If the buffer layer is p-type SiC, in particular embodiments, the p-type epitaxial layer may be formed by forming a first p-type epitaxial layer on the substrate and forming a second p-type epitaxial layer on the first p-type epitaxial layer, wherein the second p-type epitaxial layer has a lower dopant concentration than the first p-type epitaxial layer.

In still further embodiments, an ohmic contact is formed to the p-type epitaxial layer. Furthermore, p-type dopants may be implanted in the p-type epitaxial layer so as to provide a region of p-type conductivity silicon carbide having a higher carrier concentration than the p-type epitaxial layer the ohmic contact formed on the implanted region. The ohmic contact may be formed by etching a ground contact window through the cap layer and the n-type epitaxial layer in a region adjacent a source region of the MESFET and forming the ohmic contact in the ground contact window.

The advantages and features of the invention, and the manner in which the same are accomplished, will become more readily apparent upon consideration of the following detailed description of the invention taken in conjunction with the

accompanying drawings, which illustrate preferred and exemplary embodiments, and wherein:

DESCRIPTION OF THE DRAWINGS

5 **FIG. 1** is a cross-sectional view of one embodiment of the present invention having source and drain regions formed directly on the drift layer;

FIG. 2 is a cross-sectional view of a second embodiment of the present invention having a selectively doped isolation layer and n^+ regions formed in the n-type epitaxial layer;

10 **FIG. 3A** is a cross-sectional view of a third embodiment of the present invention having a recessed mushroom gate structure;

FIG. 3B is a cross-sectional view of a fourth embodiment of the present invention having a double recessed gate structure;

FIG. 4 is a cross-sectional view of a passivation layer structure according to a preferred embodiment of the present invention;

15 **FIG. 5** is a cross-sectional view of a metallization structure according to an embodiment of the present invention;

FIGs. 6A through 6I illustrate processing steps in the fabrication of MESFETS according to various embodiments of the present invention;

20 **FIG. 7** is a curve tracer plot of the family of DC curves for a 1-mm SiC MESFET having a p-type epitaxial layer doped to an acceptor impurity density (N_A) $< 5 \times 10^{15} \text{ cm}^{-3}$;

FIG. 8 is a curve tracer plot of the family of DC curves for a 1-mm SiC MESFET having a p-type epitaxial layer doped to $N_A = 9 \times 10^{16} \text{ cm}^{-3}$;

25 **FIG. 9** is a cross-sectional view of one embodiment of the present invention having a ground contact to the buffer layer;

FIG. 10 illustrates the electron distribution in a SiC MESFET as determined with a two-dimensional Monte-Carlo simulation;

FIG. 11 illustrates drain current as a function of RF drive in a SiC MESFET;

30 **FIG. 12** is an illustration of drain current of a MESFET under pulsed operation where the envelope of the bias voltage is longer than the envelope of the RF signal;

FIG. 13 illustrates on-wafer power measurement of a 0.25-mm SiC MESFET fabricated on a vanadium-doped semi-insulating substrate showing a power density of 5.6 W/mm at 3.5 GHz; and

FIG. 14 illustrates on-wafer power measurement of a 0.25-mm SiC MESFET fabricated on a vanadium-free semi-insulating substrate showing a power density of 5.2 W/mm at 3.5 GHz.

DETAILED DESCRIPTION

The present invention will now be described with reference to the Figures which illustrate various embodiment of the present invention. As illustrated in the Figures, the sizes of layers or regions are exaggerated for illustrative purposes and, thus, are provided to illustrate the general structures or the present invention. Furthermore, various aspects of the present invention are described with reference to a layer being formed on a substrate or other layer. As will be appreciated by those of skill in the art, references to a layer being formed on another layer or substrate contemplates that additional layers may intervene. References to a layer being formed on another layer or substrate without an intervening layer are described herein as being for "directly" on the layer or substrate. Like numbers refer to like elements throughout.

FIG. 1 illustrates a first embodiment of a MESFET of the present invention. A first epitaxial layer 12 of p-type conductivity is grown on a single crystal bulk silicon carbide substrate 10 of either p-type or n-type conductivity or semi-insulating. The first epitaxial layer of silicon carbide 12 is disposed between the substrate 10 and an n-type epitaxial layer 14. An optional metallization layer, 32 may be formed on the opposite side of the substrate from the first epitaxial layer 12. The metallization layer 32 is preferably formed as described below with reference to **FIG. 5**.

The first epitaxial layer 12 may be a p-type conductivity silicon carbide epitaxial layer, an undoped silicon carbide epitaxial layer or a very low doped n-type conductivity silicon carbide epitaxial layer. If a low dope silicon carbide epitaxial layer is utilized, then it is preferred that the doping concentration of the first epitaxial layer 12 be less than about $5 \times 10^{15} \text{ cm}^{-3}$. If an undoped or n-type first epitaxial layer 12 is utilized, the substrate 10 is preferably a semi-insulating silicon carbide substrate. If an undoped or n-type first epitaxial layer 12 is utilized, a high quality channel layer

may be formed without the buffer layer having any significant electrical effect on the transistor.

Ohmic contacts 20 and 22, are formed directly on the second epitaxial layer 14 and are spaced apart so as to provide a source contact 20 and a drain contact 22. A Schottky gate contact 24 is formed directly on the second epitaxial layer 14 between the source contact 20 and the drain contact 22. As illustrated, optional metal overlayers 26, 28 and 30 are formed on the source and drain contacts 20 and 22 and the Schottky gate contact 24. In forming the ohmic contacts 20 and 22 directly on the second epitaxial layer 14, it is preferred that these ohmic contacts 20 and 22 be formed of nickel and be annealed at about 1050 °C for about 2 minutes. However, temperatures of from about 800 to about 1150 °C and times of from about 30 seconds to about 10 minutes may also be utilized. It has been found that Ni contacts formed directly on the n-type epitaxial layer 14 may provide a contact resistance below $1 \times 10^{-6} \Omega\text{-cm}^2$. Such a low resistance may result from the use of the high temperature anneal. By forming the contacts 20 and 22 directly on the epitaxial layer 14 the need for an implantation step may be avoided. Furthermore, the surface roughness which may result from implantation and activation of ions to form the n^+ regions of conventional SiC MESFETs may be reduced. As used herein, " n^+ " or " p^+ " refer to regions that are defined by higher carrier concentration than are present in adjacent or other regions of the same or another epitaxial layer or substrate.

The structure of the transistor as shown in FIG. 1 and subsequent FIGS. 2 and 3, preferably forms a mesa which defines the periphery of the device. In a device not having a p-type epitaxial layer, the substrate and the n-type epitaxial layer form a mesa having sidewalls which define the periphery of the transistor. The sidewalls of the mesa extend downward past the n-type conductivity layer of the device. Preferably, the mesa is formed to extend into the substrate of the device. The mesa preferably extends past the depletion region of the device to confine current flow in the device to the mesa and reduce the capacitance of the device. If the depletion region of the device extends below the level of the mesa then it may spread to areas outside the mesa, resulting in larger capacitance. The mesa is preferably formed by reactive ion etching the above described device, however other methods known to one skilled in the art may be used to form the mesa. Furthermore, if a mesa is not utilized the device may be isolated using other methods such as proton bombardment, counterdoping with compensating atoms or others known to one skilled in the art.

FIG. 2 illustrates a second embodiment of a MESFET according to the present invention. As seen in **FIG. 2**, a selectively doped p-type epitaxial layer 12' is formed on the substrate 10. The second n-type epitaxial layer 14 is formed on the selectively doped first p-type epitaxial layer 12' and the source and drain contacts 20, 22 and Schottky metal contact 24 are formed on the n-type epitaxial layer 14. Also illustrated in **FIG. 2** are optional n^+ regions 16 and 18 formed in the source and drain regions of the device. If the n^+ regions 16 and 18 are formed, it is preferred that these regions be formed by ion implantation of preferably phosphorous (P), although nitrogen (N) may also be used, followed by a high temperature anneal. Suitable anneal temperatures may be from about 1100 to about 1600 °C.

Alternatively, the n^+ regions 16 and 18 may be eliminated as described above so as to provide a device having the source, drain and gate structure illustrated in **FIG. 1**. In such a case, it is preferred that the ohmic contacts 20 and 22 be formed as described above with reference to **FIG. 1**. As illustrated, optional metal overlayers 26, 28 and 30 are formed on the source and drain contacts 20 and 22 and the Schottky gate contact 24. Also illustrated is a metallization layer 32 formed on substrate 10. The metallization layer 32 is preferably formed as described below with reference to **FIG. 5**.

FIG. 3A illustrates a third embodiment of a MESFET of the present invention where the Schottky gate contact 40 is recessed in the active channel layer. **FIG. 3A** also illustrates an embodiment of the present invention where the Schottky gate contact 40 is a mushroom gate contact. A first epitaxial layer 13 of p-type conductivity is grown on a single crystal bulk silicon carbide substrate 10 of either p-type conductivity, n-type conductivity or semi-insulating. The p-type epitaxial layer 13 may be a lightly doped p-type layer 12 as illustrated in **FIG. 1** or a selectively doped p^+ layer 12' as illustrated in **FIG. 2**. A second epitaxial layer 14 of n-type conductivity is grown on the first epitaxial layer 13. Also illustrated in **FIG. 3A** are optional n^+ regions 16 and 18 formed in the source and drain regions of the device which may be formed as described with reference to **FIG. 2**. The n^+ regions 16 and 18 may be eliminated as described above with reference to **FIG. 2** and illustrated in **FIG. 1**. Ohmic contacts 20 and 22, are formed on wells 16 and 18 to create a source contact and a drain contact. A portion of the second epitaxial layer 14 is removed to provide a recessed section between the source and the drain. A Schottky gate contact

40 is formed in the recessed portion of the second epitaxial layer 14 between the source and drain contacts.

The Schottky gate contact 40 is a mushroom structure. As used herein a mushroom gate is a gate structure at least a portion of which has increasing cross-sectional area as the distance from the second epitaxial layer 14 increases. Preferably, the gate structure is self aligned with respect to the recess in the n-type layer 14. Furthermore, it is preferred that the recess be formed by dry etching and more particularly formed by Electron Cyclotron Resonance (ECR) or Inductively Coupled Plasma (ICP) etching. Forming a self-aligned recess for formation of the gate in such a manner may result in low damage to the epitaxial layer and any insulating layer as well as provide high breakdown characteristics.

Another method of forming the recessed gate is to perform the etching in two steps with a double recess process as illustrated in FIG. 3B. As seen in FIG. 3B, the Schottky gate contact 40 is formed in a double recess through a cap layer 15 and into the second epitaxial layer 14. The cap layer 15 may be first etched through and then a second etch performed to etch into the second epitaxial layer 14. The first etch can be performed either through the cap layer 15 that is doped at the same level as in the n-type epitaxial layer 14 or it can be very lightly n-type doped, with the preferred doping range for the cap layer 15 being $N_D = \text{about } 1 \times 10^{15} \text{ cm}^{-3} \text{ to about } 5 \times 10^{17} \text{ cm}^{-3}$ and the preferred thickness of this cap layer being from about 50 nm to about 300 nm. The depth of the first etch can be all the way through the cap layer 15, or it may be only partially through the cap layer 15. The preferred depth into the second epitaxial layer 14 for the second etch is from about 20 nm to about 120 nm. The cap layer 15 may be formed as part of the epitaxial growth process of the second epitaxial layer 14, however, the doping concentration may be changed to provide the preferred doping range for the cap layer 15. Thus, the cap layer 15 may be a separate layer or may be part of the second epitaxial layer 14.

The two etch approach may have a number of advantages over a single recess process. One advantage is that the first etch can be performed prior to any metalization on the wafer, allowing a thermal oxide to be grown subsequent to etching. The thermal oxidation process removes SiC that may have been damaged by the etch process and also smoothes out roughness that may have been created on the surface by the etch. This may enable the second etch, performed immediately prior to

the gate metalization, to be much shallower, minimizing the sub-surface damage and surface roughness that, typically, cannot be removed. Another advantage of the double recess process is that the shallower second etch reduces the amount of gate contact to the etched side wall. This minimizes the contact area with potentially
5 damaged material and the reduced contact area may also reduce the gate capacitance and, therefore, improve the frequency response of the transistor.

As illustrated, the Schottky mushroom gate contact 40 can optionally be formed of a first gate layer 42 of chromium (Cr) contacting the active channel layer, a barrier layer 44 of platinum (Pt) and a third layer of gold 46 or other highly
10 conductive metal. Preferably, the chromium layer 42 is formed by evaporative deposition.

As is further illustrated, an optional metal overlayer 26 and 28 is formed on the source and drain contacts. Preferably, the metal overlayer 26 and 28 is formed of titanium (Ti) for adhesion to a nickel contact, platinum (Pt) as a barrier layer and gold
15 (Au) as a highly conductive metal.

An optional metallization layer 32 may be formed on the opposite side of the substrate 10 from epitaxial layer 13 to provide a conducting plane on the substrate 10. The metallization layer is preferably formed as described below with reference to
FIG. 5.

20 **FIG. 4** illustrates a preferred embodiment of the passivation layer 60 of **FIG. 1** through 3. Such a passivation layer may be formed as described in United States Patent No. 5,972,801, the disclosure of which is incorporated herein by reference as if set forth fully herein. Prior to formation of contacts 20, 22, 24 and 40, the upper surface of the device is preferably passivated with an Oxide-Nitride-Oxide (ONO)
25 passivation layer 60. As seen in **FIG. 4**, the upper surface of the structure is passivated by growing a thermal oxide layer 60A of SiO_2 , followed by depositing a Si_3N_4 layer 60B using PECVD or LPCVD, followed by a final layer of thermally grown SiO_2 60C. Prior to growing the SiO_2 layer, the wafer is annealed in a high temperature H_2 ambient. Temperatures of greater than about 900 °C for from about
30 15 minutes to about 2 hours may be utilized for the anneal, however, a temperature of about 1100 °C for about 30 minutes is preferred. The ONO passivation layer enables the device to have better power density, primarily due to decreased trapping from the surface. ONO has lower interface trap density (D_{it}) near the conduction band.

Preferably, the passivation layer 60 is formed by first forming an SiO₂ layer 60A of about 200 Å through a dry oxide process at about 1200 °C. The first layer 60A is then argon annealed for about 1 hour at about 1200 °C. This is subsequently oxidized at about 950 °C for about 180 minutes in a wet environment. Then layer 60B of Si₃N₄ of about 500 Å thickness is deposited by PECVD or LPCVD. Then a final oxidation is performed at about 950 °C for about 180 minutes in a wet environment to provide the third layer 60C of oxide. While these fabrication specifications are preferred, other suitable conditions and specifications may also be utilized. For example, the first layer 60A may have a thickness of from about 50 to about 500 Å, the second layer 60B may have a thickness of from about 200 to about 2,000 Å and the third layer 60C may have a thickness of from about 20 to about 200 Å. Similarly, the processing conditions may be varied to provide the thickness described above. Through combination of a self-aligned recessed gate and ONO surface passivation, the RF power density may be increased and the amount of drift in the RF performance as the drive level changes may be greatly reduced.

In further embodiments of the present invention, the passivation layer 60 may be a thermally grown or deposited oxide. In either case, the oxide is preferably annealed at from about 1000 °C to about 1300 °C for from about 30 to about 300 minutes in a NO ambient. Such an anneal may reduce interface trap density near the conduction band and, thereby, improve the high frequency performance of the device. In a particularly preferred embodiment of the present invention, the passivation layer 60 is fabricated as described above with reference to FIG. 4 to provide an ONO layer. Preferably, however, the thermal oxide layer 60A is annealed at from about 1000 °C to about 1300 °C for from about 30 to about 300 minutes in a NO ambient prior to depositing the Si₃N₄ layer 60B.

FIG. 5 illustrates a preferred embodiment for the metallization layer 32 of FIG. 1 through 3. As seen in FIG. 5, the metallization layer 32 is deposited on the back plane of the substrate 10. Prior to formation of the metallization layer, the wafer is preferably thinned to about 100 μm or less and possibly as low as 50 μm or 25 μm in thickness by a mechanical thinning process such as grinding or lapping. The metallization layer 32 may include a layer 50 of TiPtAu coated with an overlayer 52 of a eutectic alloy of AuGe. The use of such a metallization layer 32 can improve the device packaging by permitting easier attachment of the device to a circuit board.

Furthermore, by thinning the wafers before metallization, the thermal performance of the device may be improved.

In each of the embodiments described above, the substrate may be formed of silicon carbide selected from the group of 6H, 4H, 15R or 3C silicon carbide and the epitaxial layers may be formed of silicon carbide selected from the group of 6H, 4H, 15R or 3C silicon carbide. The substrate 10 may be formed of single crystal bulk silicon carbide and may be semi-insulating or either p-type or n-type conductivity. The first epitaxial layers 12, 12' and 13 may be formed of p-type conductivity silicon carbide of 6H, 4H, 15R or 3C polytype. Carrier concentrations of from about 1×10^{16} to about $1 \times 10^{17} \text{ cm}^{-3}$ are suitable for the first epitaxial layer if the first epitaxial layer 12' is selectively doped, however, carrier concentrations of about 3 to 5×10^{16} are preferred. Suitable dopants include aluminum, boron and gallium. The first epitaxial layer 12' is preferably selectively doped to provide a total charge density of greater than about $1 \times 10^{12} \text{ cm}^{-2}$. Preferably, first epitaxial layer 12' has a thickness of from about $0.5 \text{ }\mu\text{m}$ to about $2 \text{ }\mu\text{m}$. As described above, the first epitaxial layer 12 may also be undoped or lightly doped n-type silicon carbide.

The second epitaxial layer 14 may be formed of n-type conductivity silicon carbide of 6H, 4H, 15R or 3C polytype. N-type carrier concentrations of the n-type epitaxial layer from about 2×10^{16} to about $2 \times 10^{18} \text{ cm}^{-3}$ are suitable. Suitable dopants include nitrogen and phosphorous, however, nitrogen is preferred. For the optional n^+ regions of the transistors described above, carrier concentrations of about 5×10^{17} are suitable but carrier concentrations of about 2×10^{18} or higher are preferred. The ohmic contacts 20 and 22 are preferably formed of nickel or other suitable metals. The Schottky gate contacts 24 may be formed of chromium, platinum or platinum silicide, nickel, or TiWN however other metals such as gold, known to one skilled in the art to achieve the Schottky effect, may be used. Preferably, however, the Schottky gate contact 24 has the three layer structure described with regard to the mushroom gate 40. Such a structure may have advantages because of the high adhesion of chromium (Cr). The above described devices optionally have an overlayer on one or more of the ohmic contacts and the gate contact, the overlayer 26, 28 and 30 as described above but may also be gold, silver, aluminum, platinum and copper. Other suitable highly conductive metals may also be used for the overlayer.

The thickness of the n-type conductivity region beneath the gate contact defines the cross-sectional height of the channel region of the device and is selected based on the desired pinch-off voltage of the device and the carrier concentration. Given the carrier concentration of the second epitaxial layer, the depth of the layer for a given pinch-off voltage may be readily calculated using methods known to one skilled in the art. Accordingly, it is desirable for the thickness and carrier concentration of the n-type epitaxial layer to be selected to provide a pinch-off voltage of greater than -3 volts and preferably greater than -5 volts. The pinch off voltage may also be from between about -3 volts and -20 volts, but preferably between about -5 volts and -15 volts. For a device utilizing an n-type substrate, the thickness of the buried p-type conductivity layer of the above-described devices should be sufficiently thick so that breakdown of the gate junction occurs before the depletion of the p-type conductivity layer. For a device utilizing a p-type substrate, the thickness of the buried p-type conductivity layer and the substrate of the above described devices should be sufficiently thick so that breakdown of the gate junction occurs before the depletion of the p-type conductivity layer and the substrate.

The above descriptions describe the preferred embodiments of the present invention, however, the first epitaxial layer described above may optionally be eliminated and thereby forming a transistor having a single epitaxial layer of n-type conductivity SiC formed on either a semi-insulating substrate or a p-type substrate. In forming a single epitaxial layer device, the substrate of the device it is preferable to utilize either p-type conductivity silicon carbide having the carrier concentrations as described for the p-type buried layer or a semi-insulating substrate.

In selecting the dimensions of the MESFET, the width of the gate is defined as the dimension of the gate perpendicular to the flow of current. As shown in the cross-sections, FIGS. 1 through 3B, the gate width runs into and out of the page. The length of the gate is the dimension of the gate parallel to the flow of current. As seen in the cross-sectional views of FIGS. 1 through 3B, the gate length is the dimension of the gate 24 which is in contact with the second epitaxial layer 14. A third important dimension is the source to gate distance which is shown in the cross-sections, FIG. 1 through 3, as the distance from the source contact 20 or n^+ region 16 if present, to the gate contact 24.

To minimize the effect of low electron mobility, the source to gate distance should be as small as possible without allowing substantial source to gate leakage

current. In one embodiment of the present invention, the distance from the source to the Schottky gate contact is large enough to prevent the flow of any substantial leakage current from the source to the gate when a bias is applied to the gate while small enough to minimize the effect of the low electron mobility of silicon carbide.

- 5 This typically means that the gate contact should be as close to the source contact without coming into contact with the source contact or the n^+ region if present. Positioning the gate as close as possible to the source region can maximize the electric field intensity in the region of the transistor where the electrons are accelerated and thereby reduces the effect of low electron mobility of SiC. Typically, the distance
- 10 from the source to the Schottky contact of about 1 μm or less, is desirable. The gate to drain distance of the device should be large enough to support the gate to drain depletion spread of the device. These distances are typically from about 0.5 μm to about 5 μm .

- To further minimize the effect of low electron mobility, the length of the gate
- 15 contact should be as small as possible. Typically, Schottky gate lengths of less than about 1.0 μm are desirable. By minimizing the length of the gate, the intensity of the electric field beneath the gate is increased. The increase in electric field results because the same voltage is placed across a smaller area. This increase in electric field intensity increases the acceleration of the electrons in the gate area and thereby
- 20 reduces the effects of the low electron mobility of silicon carbide. Thus, it is desirable to minimize the length of the gate and thereby maximize the intensity of the electric field beneath the gate.

- If the first epitaxial layer 12' is selectively doped, then the substrate 10 may also be doped with a deep level dopant such as vanadium to create a semi-insulating
- 25 substrate. While conventional techniques for forming semi-insulating silicon carbide may be utilized with particular embodiments of the present invention, as is described below, preferably, the semi-insulating substrate is fabricated without deep level dopants.

- FIGs. 6A through 6I** illustrate processing steps which may be utilized in
- 30 producing FETs according to various embodiments of the present invention. As seen in **FIG. 6A**, a p-type epitaxial layer 13 is formed on a SiC substrate 10 as described above. Preferably, the substrate 10 is a semi-insulating SiC substrate and the p-type

epitaxial layer 13 is selectively doped to a carrier concentration of from about 1×10^{16} to about $1 \times 10^{17} \text{ cm}^{-3}$ and more preferably from about 3×10^{16} to about $5 \times 10^{16} \text{ cm}^{-3}$.

Preferably, the substrate 10 is semi-insulating with no intentional doping of deep level dopants such that the resistivity of the substrate is not dominated by deep level dopants. Such substrates may be fabricated as described in commonly assigned and co-pending United States Patent Application Serial No. 09/313,802 entitled "Semi-insulating Silicon Carbide Without Vanadium Domination", the disclosure of which is incorporated herein as if set forth fully. Such a semi-insulating substrate may be produced by providing silicon carbide substrates which sufficiently high levels of point defects and sufficiently matched levels of p-type and n-type dopants such that the resistivity of the silicon carbide substrate is dominated by the point defects. Such a domination may be accomplished by fabricating the silicon carbide substrate at elevated temperatures with source powders which have concentrations of heavy metals, transition elements or other deep level trapping elements of less than about $1 \times 10^{16} \text{ cm}^{-3}$ and preferably less than about $1 \times 10^{14} \text{ cm}^{-3}$. For example, temperatures between about 2360 °C and 2380 °C with the seed being about 300 °C to about 500 °C lower may be utilized. Thus, it is preferred that the semi-insulating substrate be substantially free of heavy metal, transition element dopants or other deep level trapping elements, such as vanadium, such that the resistivity of the substrate is not dominated by such heavy metals or transition elements. While it is preferred that the semi-insulating substrate be free of such heavy metal, transition element dopants or deep level trapping elements, such elements may be present in measurable amounts while still benefiting from the teachings of the present invention if the presence of such materials does not substantially affect the electrical properties of the MESFETs described herein. Accordingly, as used herein, the term "substantially free of deep level dopants" refers to concentrations of heavy metals, transition elements or deep level trapping elements which do not substantially affect the electrical properties of a MESFET according to embodiments of the present invention. For example, a substrate with a concentration of heavy metal, transition element or deep level trapping element, such as vanadium, of less than $1 \times 10^{17} \text{ cm}^{-3}$ may be considered substantially free of deep level dopants.

As seen in FIG. 6B, an n-type epitaxial layer 14 is formed on the p-type epitaxial layer 13 as described above with reference to FIGs. 1 through 3. As is also shown in FIG. 6B, the substrate and epitaxial layers are etched to form an isolation

mesa and an ONO passivation layer 60 is formed on the mesa, including the n-type epitaxial layer 14. Preferably, the ONO passivation layer 60 is formed as described above with reference to FIG. 4.

As described above, optionally a cap layer 15 may be formed on or as part of the n-type epitaxial layer 14. Thus, in these alternative embodiments, the cap layer 15 may be formed prior to formation of the ONO passivation layer 60. Furthermore, the first etch of the double recess may be performed before formation of the ONO passivation layer 60. The formation of the ONO passivation layer may also be preceded by a thermal oxidation of the SiC cap layer 15 and any exposed portions of the n-type epitaxial layer 14 and a wet etch to remove the oxidation. The process may continue as described below for the single recess embodiments of the present invention.

As seen in FIG. 6C, openings may be formed in the ONO layer 60 and n^+ wells 16 and 18 implanted in the n-type epitaxial layer 14 and annealed to activate the implant. Nickel may then be evaporated to deposit the source and drain contacts 20 and 22 and annealed to form the ohmic contacts. Such a deposition and annealing process may be carried out utilizing conventional techniques known to those of skill in the art. FIG. 6C also illustrates the formation of the overlayer 26 and 28 as described above. As will also be appreciated by those of skill in the art, the overlayer may be formed either before or after formation of the Schottky gate structure. In fact, if the titanium/platinum/gold structure described above is utilized the platinum and gold portions of the overlayer may be formed in the same processing steps as the platinum and gold portions of the Schottky gate structure. Accordingly, while the overlayer 26 and 28 is illustrated as being formed prior to the formation of a recess or gate contact, the present invention should not be construed as limited to such a sequence.

FIG. 6D illustrates the formation of a recess for the gate structure of the MESFET. The ONO layer 60 may be etched through and the n-type epitaxial layer 14 etched into to form the recess 100 for the gate structure. Preferably, the recess 100 is formed by the etching process described above. Subsequently, the ONO layer may be patterned to provide the "T" shaped top of the gate structure by providing the ledge portions 102 of the recess sidewalls. A layer of chromium 42 may then be deposited in the recess as described above and illustrated in FIG. 6E. The gate structure may

then be completed by deposition of the platinum layer 44 and the gold layer 46 as illustrated in FIG. 6F.

FIG. 6G illustrates the formation of a Si_3N_4 layer 110 on the wafer. FIG. 6G also illustrates that the substrate 10 may be thinned as described above to provide a thinned substrate 10'. The metallization 32 may then be formed on the thinned substrate 10' as illustrated in FIG. 6I. Contact holes may also be formed through the Si_3N_4 layer 110 so as to allow contact between the source, drain and gate contacts and a metallized interconnect layer (not shown).

The invention and its possible advantages will be further understood through the following example. MESFETs were processed as follows: Epitaxial layers were grown on a semi-insulating 4H-SiC wafer with a p-type buffer layer 0.5 μm thick doped and an n-type channel layer 0.28 μm thick and doped. Source and drain n^+ wells were formed by ion implantation of phosphorus that was activated with an anneal at 1300°C for 1 hour. Isolation mesas were then etched, followed by ONO passivation as described above. Ohmic contacts were then formed by etching the ONO off the n^+ wells, evaporating Ni and annealing at 1050°C. The 0.7 μm gates were formed with a self-aligned recess etch through the ONO and 500 Å into the channel. A second photolithography step was used to pattern a T-top, and then the Schottky contact was formed with an evaporation of 250 Å of Cr, 500 Å of Pt and 7500 Å of Au. After gate formation, 1,000 Å of Si_3N_4 is deposited by PECVD at 350°C.

FIG. 8 is a curve tracer plot of the family of DC curves for a 1-mm SiC MESFET as described above. As can be seen from FIG. 8, the MESFET has reduced output conductance and shows excellent pinch-off out to a drain bias of 200 V. The advantages of the selective doping in the buffer layer are best illustrated by examining the DC I-V characteristics of MESFETs fabricated with a p-type buffer doping of $N_A < 5 \times 10^{15} \text{ cm}^{-3}$ (FIG. 7) and $N_A = 9 \times 10^{16} \text{ cm}^{-3}$ (FIG. 8). As shown in FIG. 7, with a lightly doped p⁻ buffer layer design, an extra 6 to 8 V of gate bias is required to keep the channel current pinched off as the drain bias is increased, and the output conductance ($\Delta I_D / \Delta V_D$) is high. By increasing the doping in the buffer to $N_A = 9 \times 10^{16} \text{ cm}^{-3}$, better current confinement was achieved, as shown in FIG. 8. The output conductance has been reduced by a factor of 3 and the gate voltage required to pinch the device off at $V_{ds} = 200 \text{ V}$ is only 2 V more than is required at $V_{ds} = 10 \text{ V}$.

Thus, both the gain and efficiency of the MESFET may be improved. MESFETs measured on the wafer with I-V curves shown in FIG. 8 had an increase in power gain of 3 dB at 3.5 GHz as compared to MESFETs measured from the wafer with I-V curves shown in FIG. 7.

5 Further improvements to the DC characteristics of the MESFETs according to embodiments of the present invention have been demonstrated by forming a ground contact 29 to the highly doped p-type buffer layer 12' on the source side of the channel as illustrated in FIG. 9. This ground contact 29 may eliminate one of the potential drawbacks of having a p-type buffer layer which is not fully depleted, which is that hole charge can build up and be stored in this layer. This undesired buildup of
10 hole charge may be prevented by providing a ground path for the holes. Because of the difficulty in making high quality ohmic contacts to p-type SiC, it is preferred that the p⁺ contact wells be formed in the buffer layer by etching off the n-type channel and implanting the buffer layer with a p-type dopant, such as Al, and activating the
15 implanted species at a temperature of between about 1550 °C and about 1750 °C to provide a p⁺ well 17 in the buffer layer 12'. This p-type contact 29 should be as close to the channel as possible without interfering with the n-type source ohmic contact 20. The p-type ohmic contact 29 may be formed with the same step as the n-type ohmic contacts in order to reduce processing steps. It may also be formed in a separate step
20 using a process designed to minimize ohmic contact resistance to the p-type material. An example of such a process is to deposit Ni with a thickness in the range of from about 500 Å to about 1500 Å and anneal the contacts with a rapid thermal anneal at a temperature in the range of from about 550 °C to about 900 °C.

The series resistance of the p-type buffer layer can be reduced by increasing
25 the doping in this layer, but this may have an adverse effect on the frequency response and breakdown voltage of the MESFET. A method of obtaining the advantage of the heavily doped p-type layer without compromising the performance of the MESFET is to form the p-type buffer layer 12' with two layers as illustrated in FIG. 9. The bottom layer 12'' may be doped with N_A greater than about $5 \times 10^{18} \text{ cm}^{-3}$ and be from
30 about 0.5 to about 2.0 μm thick to provide a region with low resistance, followed by a layer 12''' with N_A between about $5 \times 10^{16} \text{ cm}^{-3}$ to about $5 \times 10^{17} \text{ cm}^{-3}$ with a thickness of from about 0.75 to about 2.0 μm that reduces the output conductance of the FET and still supports drain voltages in excess of 200 V. The quality of the p-type

ohmic contact may be further improved by forming the implanted p^+ well 17 in the heavily doped bottom layer 12".

While embodiments of the present invention incorporating a contact to the buried p-type layer 12' have been described with reference to FIG. 9, as will be appreciated by those of skill in the art, the p-type contact may also be provided in any of the other embodiments described herein having a p-type epitaxial layer. Thus, the present invention should not be construed as limited to the embodiments illustrated in FIG. 9.

As is briefly described above, MESFETs according to preferred embodiments of the present invention utilize semi-insulating SiC substrates. One method of forming semi-insulating substrates is to intentionally incorporate a deep level dopant into the lattice in order to pin the Fermi level at a very deep energy level relative to the conduction band. These deep level dopants act as trap centers for any electrons that get injected into the substrate under normal device operation. This trapping may have a substantial impact on the performance of microwave MESFETs because the time constants associated with these traps are much slower than the frequency at which the devices are being operated, so the amount of trapped charge increases over time and alters the behavior of the transistor.

FIG. 10 shows the charge distribution in a cross-sectional region of a SiC MESFET that was determined with a two-dimensional Monte-Carlo simulation. The structure that was modeled consisted of a semi-insulating 4H-SiC substrate, a thin p^- buffer layer and an n-type channel region 0.25 μm thick with a doping of $N_D = 3 \times 10^{17} \text{ cm}^{-3}$. The simulations show that under high drain bias voltages there is a significant amount of charge that is pulled into the substrate because of the high electric field between the source and drain regions. This charge can be trapped in the substrate, and as the amount of negative charge beneath the active region of the MESFET increases, the channel becomes depleted from the back side, reducing the amount of current that can flow in the transistor.

This back-gating effect may impact the operation of MESFETs in several different ways. The first is that the peak RF power available from the device is typically lower than is expected from the DC characteristics of the device because the peak current available under RF drive is reduced by the trapped charge below the channel. Secondly, the efficiency of the part is, typically, not as high as it should be

because the ratio of peak to average current is reduced for the same reason. The trapping effects may also change the bias conditions of the part under RF operation as the back-gating charge is accumulated. FIG. 11 illustrates one of these bias shifts that has been observed. In an ideal MESFET, the drain current increases monotonically under RF drive and then returns to the quiescent value when the RF drive is removed. In SiC MESFETs with the presence of deep level traps, the drain current initially droops below the quiescent value as RF drive is increased, thereby reducing the power, linearity and efficiency of the device. An additional problem is that when the RF power is removed, the drain current drops well below the quiescent value and may take several minutes to recover to the original value. Because this is caused by deep level traps, the recovery time can be reduced either by heating the device or by shining light on it.

FIG. 12 illustrates another problem with the drain current that has been observed while the MESFETs were being operated in pulsed mode. In pulsed operation, the bias to the device is removed while the RF signal is not present in order to minimize heating and then restored to the device just prior to the beginning of the next RF pulse. In MESFETs fabricated on semi-insulating SiC substrates with high levels of deep level dopants, the current drawn by the device prior to the RF pulse is a function of the amount of RF drive in the preceding pulse. This memory effect implies that charge is being stored somewhere in the device. As seen in FIG. 12, waveform (a) shows the drain current under a low level of RF drive, where the current increases while the RF pulse is on. Waveform (b) shows the same MESFET under high RF drive where the current outside the RF envelope is lower than it was under low RF drive, which is a back-gating effect due to trapped charge. Waveform (c) shows the ideal waveform where the current outside of the applied RF signal is independent of the drive level. Both of these bias shift phenomena can be reduced or eliminated by fabricating MESFETs according to embodiments of the present invention with a recessed gate, either single or double recess, on semi-insulating wafers that have no intentional doping with vanadium, which is the dominant deep-level dopant commonly used to form semi-insulating SiC.

Additionally, the efficiency of the devices was improved, as shown by the comparison of on-wafer power measurements in FIG. 13 and FIG. 14. The measurements illustrated in FIG. 13 and FIG. 14 were made at 3.5 GHz on 0.25-mm SiC MESFETs with a gate length of 0.7 μm . The MESFET fabricated on the

vanadium-free substrates (FIG. 14) had a much improved power added efficiency of 63% compared to the 35% efficiency of the MESFET fabricated on the vanadium-doped substrates (FIG. 13) while maintaining a comparable power density of > 5 W/mm. The improvement in efficiency may result from the ability to bias the
5 transistor at a much lower quiescent drain current and still obtain the same amount of peak power.

In the drawings and specification, there have been disclosed typical preferred embodiments of the invention and, although specific terms are employed, they are used in a generic and descriptive sense only and not for purposes of limitation, the
10 scope of the invention being set forth in the following claims.

That which is claimed is:

1. A metal-semiconductor field-effect transistor comprising:
a semi-insulating silicon carbide substrate which is substantially free of deep level dopants;
an n-type epitaxial layer of n-type conductivity silicon carbide on the
5 substrate,
ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain; and
a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain to form an active
10 channel in the n-type epitaxial layer between the source and the drain when a bias is applied to the Schottky metal contact.
2. A metal-semiconductor field-effect transistor according to Claim 1, wherein the semi-insulating substrate has a level of deep level dopants which is below a level which dominates the resistivity of the substrate.
3. A metal-semiconductor field-effect transistor according to Claim 1, wherein the semi-insulating silicon carbide substrate has less than about $1 \times 10^{16} \text{ cm}^{-3}$ of heavy metals, transition elements and deep level trapping elements.
4. A metal-semiconductor field-effect transistor according to Claim 1, wherein the semi-insulating silicon carbide substrate has less than about $1 \times 10^{14} \text{ cm}^{-3}$ of heavy metals, transition elements and deep level trapping elements.
5. A metal-semiconductor field-effect transistor according to Claim 1, further comprising:
a cap layer of n-type silicon carbide on the n-type epitaxial layer;
a first recess in the cap layer;
5 a second recess in the n-type epitaxial layer, wherein the recess in the n-type epitaxial layer is within the first recess in the cap layer
a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain to form an active channel in the n-type epitaxial layer between the source and the drain when a bias is

- 10 applied to the Schottky metal contact wherein the Schottky metal contact is within the recess in the n-type epitaxial layer.

6. A metal-semiconductor field-effect transistor according to Claim 5, wherein the n-type epitaxial layer and the cap layer have carrier concentrations which are substantially the same.

7. A transistor according to Claim 5, wherein the recess in the n-type epitaxial layer extends to a depth of from about 20 nm to about 120 nm.

8. A transistor according to Claim 5, wherein the cap layer has a dopant level from about $1 \times 10^{15} \text{ cm}^{-3}$ to about $5 \times 10^{17} \text{ cm}^{-3}$.

9. A transistor according to Claim 5, wherein the cap layer has a thickness of from about 50 nm to about 300 nm.

10. A transistor according to Claim 1, wherein the ohmic contacts are directly on the n-type epitaxial layer.

11. A transistor according to Claim 1, further comprising regions of n^+ silicon carbide between the n-type epitaxial layer and the ohmic contacts.

12. A transistor according to Claim 1, wherein the ohmic contacts comprise nickel contacts directly on the n-type epitaxial layer.

13. A transistor according to Claim 1 further comprising an overlayer on the ohmic contacts and the Schottky metal contact.

14. A transistor according to Claim 13, wherein the ohmic contacts comprise nickel and wherein the overlayer comprises layers of titanium, platinum and gold.

15. A transistor according to Claim 1, wherein the n-type epitaxial forms a mesa having sidewalls extending through the n-type layer which define the periphery of the transistor.
16. A transistor according to Claim 15 wherein the mesa further comprises the substrate and the sidewalls of the mesa extend into the substrate.
17. A transistor according to Claim 15, further comprising a passivation layer on the sidewalls of the mesa and exposed portions of the n-type epitaxial layer.
18. A transistor according to Claim 17, wherein the passivation layer is an ONO passivation layer.
19. A transistor according to Claim 1, further comprising metallization formed on the substrate opposite the n-type layer.
20. A transistor according to Claim 19, wherein the substrate has a thickness of about 100 μm or less.
21. A transistor according to Claim 19, wherein the metallization comprises layers of titanium, platinum and gold coated with an overlayer of eutectic alloy of AuGe.
22. A transistor according to Claim 1 wherein the Schottky metal contact comprises a first gate layer of chromium directly on the n-type epitaxial layer.
23. A transistor according to Claim 22, wherein the Schottky metal contact further comprises an overlayer on the first gate layer, wherein the overlayer comprises layers of platinum and gold.
24. A transistor according to Claim 23, wherein the Schottky metal contact is a mushroom gate.

25. A transistor according to Claim 24, further comprising a recess in the n-type epitaxial layer and wherein the first gate layer is formed in the recess in the n-type epitaxial layer.

26. A transistor according to Claim 24, wherein the mushroom gate is self aligned with respect to the recess.

27. A transistor according to Claim 1, further comprising an undoped silicon carbide buffer layer formed between the substrate and the n-type epitaxial layer.

28. A transistor according to Claim 1, further comprising an n-type conductivity silicon carbide buffer layer formed between the substrate and the n-type epitaxial layer.

29. A transistor according to Claim 1, further comprising a p-type silicon carbide buffer layer formed between the substrate and the n-type epitaxial layer.

30. A transistor according to Claim 29, further comprising an ohmic contact formed on the p-type epitaxial layer.

31. A transistor according to Claim 30, further comprising a well region of p^+ silicon carbide formed in the p-type epitaxial layer and wherein the ohmic contact is formed on the p^+ well region.

32. A transistor according to Claim 30, wherein the p-type epitaxial layer comprises:

- a first p-type epitaxial layer; and
- a second p-type epitaxial layer, wherein the first p-type epitaxial layer has a
5 doping concentration higher than a doping concentration of the second p-type epitaxial layer.

33. A metal-semiconductor field-effect transistor comprising:
a silicon carbide substrate;

- an n-type epitaxial layer of n-type conductivity silicon carbide on the substrate;
- 5 ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain;
- a cap layer of n-type silicon carbide on the n-type epitaxial layer;
- a first recess in the cap layer;
- a second recess in the n-type epitaxial layer, wherein the recess in the n-type
- 10 epitaxial layer is within the first recess in the cap layer; and
- a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain to form an active channel in the n-type epitaxial layer between the source and the drain when a bias is applied to the Schottky metal contact wherein the Schottky metal contact is within the
- 15 recess in the n-type epitaxial layer.

34. A metal-semiconductor field-effect transistor according to Claim 33, wherein the n-type epitaxial layer and the cap layer have carrier concentrations which are substantially the same

35. A transistor according to Claim 33, wherein the recess in the n-type epitaxial layer extends to a depth of from about 20 nm to about 120 nm.

36. A transistor according to Claim 33, wherein the cap layer has a dopant level from about $1 \times 10^{15} \text{ cm}^{-3}$ to about $5 \times 10^{17} \text{ cm}^{-3}$.

37. A transistor according to Claim 33, wherein the cap layer has a thickness of from about 50 nm to about 300 nm.

38. A transistor according to Claim 33, wherein the ohmic contacts are directly on the n-type epitaxial layer.

39. A transistor according to Claim 33, further comprising regions of n^+ silicon carbide between the n-type epitaxial layer and the ohmic contacts.

40. A transistor according to Claim 33, wherein the ohmic contacts comprise nickel contacts directly on the n-type epitaxial layer.
41. A transistor according to Claim 33 further comprising an overlayer on the ohmic contacts and the Schottky metal contact.
42. A transistor according to Claim 41, wherein the ohmic contacts comprise nickel and wherein the overlayer comprises layers of titanium, platinum and gold.
43. A transistor according to Claim 33, wherein the n-type epitaxial forms a mesa having sidewalls extending through the n-type layer which define the periphery of the transistor.
44. A transistor according to Claim 43 wherein the mesa further comprises the substrate and the sidewalls of the mesa extend into the substrate.
45. A transistor according to Claim 43, further comprising a passivation layer on the sidewalls of the mesa and exposed portions of the n-type epitaxial layer.
46. A transistor according to Claim 45, wherein the passivation layer is an ONO passivation layer.
47. A transistor according to Claim 33, further comprising metallization formed on the substrate opposite the n-type layer.
48. A transistor according to Claim 47, wherein the substrate has a thickness of about 100 μm or less.
49. A transistor according to Claim 47, wherein the metallization comprises layers of titanium, platinum and gold coated with an overlayer of eutectic alloy of AuGe.

50. A transistor according to Claim 33 wherein the Schottky metal contact comprises a first gate layer of chromium directly on the n-type epitaxial layer.

51. A transistor according to Claim 50, wherein the Schottky metal contact further comprises an overlayer on the first gate layer, wherein the overlayer comprises layers of platinum and gold.

52. A transistor according to Claim 51, wherein the Schottky metal contact is a mushroom gate.

53. A transistor according to Claim 52, wherein the mushroom gate is self aligned with respect to the second recess.

54. A transistor according to Claim 33, further comprising an undoped silicon carbide buffer layer formed between the substrate and the n-type epitaxial layer.

55. A transistor according to Claim 33, further comprising an n-type conductivity silicon carbide buffer layer formed between the substrate and the n-type epitaxial layer.

56. A transistor according to Claim 33, further comprising a p-type silicon carbide buffer layer formed between the substrate and the n-type epitaxial layer.

57. A transistor according to Claim 56, further comprising an ohmic contact formed on the p-type epitaxial layer.

58. A transistor according to Claim 57, further comprising a well region of p^+ silicon carbide formed in the p-type epitaxial layer and wherein the ohmic contact is formed on the p^+ well region.

59. A transistor according to Claim 57, wherein the p-type epitaxial layer comprises:

a first p-type epitaxial layer; and

a second p-type epitaxial layer, wherein the first p-type epitaxial layer has a
5 doping concentration higher than a doping concentration of the second p-type
epitaxial layer.

60. A metal-semiconductor field-effect transistor comprising:
a bulk single crystal silicon carbide substrate;
an n-type epitaxial layer of n-type conductivity silicon carbide on the
substrate;
5 a p-type epitaxial layer of selectively doped p-type conductivity silicon
carbide between the substrate and the n-type epitaxial layer, wherein the p-type
conductivity silicon carbide has a carrier concentration of from about 1×10^{16} to about
 $1 \times 10^{17} \text{ cm}^{-3}$;
ohmic contacts on the n-type epitaxial layer that respectively define a source
10 and a drain; and
a Schottky metal contact on the n-type epitaxial layer that is between the
ohmic contacts and thereby between the source and the drain to form an active
channel in the n-type epitaxial layer between the source and the drain when a bias is
applied to the Schottky metal contact.

61. A transistor according to Claim 60, wherein the p-type epitaxial layer
has a carrier concentration of from about 3×10^{16} to about $5 \times 10^{16} \text{ cm}^{-3}$.

62. A transistor according to Claim 60, wherein the ohmic contacts are
directly on the n-type epitaxial layer.

63. A transistor according to Claim 60, further comprising regions of n^+
silicon carbide between the n-type epitaxial layer and the ohmic contacts.

64. A transistor according to Claim 60, wherein the ohmic contacts
comprise nickel contacts directly on the n-type epitaxial layer.

65. A transistor according to Claim 60 further comprising an overlayer on
the ohmic contacts and the Schottky metal contact.

66. A transistor according to Claim 64, wherein the ohmic contacts comprise nickel and wherein the overlayer comprises layers of titanium, platinum and gold.

67. A transistor according to Claim 60, wherein the n-type epitaxial and p-type epitaxial layers form a mesa having sidewalls extending from the n-type layer into the p-type layer which define the periphery of the transistor.

68. A transistor according to Claim 67 wherein the mesa further comprises the substrate and the sidewalls of the mesa extend into the substrate.

69. A transistor according to Claim 67, further comprising a passivation layer on the sidewalls of the mesa and exposed portions of the n-type epitaxial layer.

70. A transistor according to Claim 69, wherein the passivation layer is an ONO passivation layer.

71. A transistor according to Claim 60, further comprising metallization formed on the substrate opposite the n-type layer.

72. A transistor according to Claim 71, wherein the substrate has a thickness of about 100 μm or less.

73. A transistor according to Claim 71, wherein the metallization comprises layers of titanium, platinum and gold coated with an overlayer of eutectic alloy of AuGe.

74. A transistor according to Claim 60 wherein the Schottky metal contact comprises a first gate layer of chromium directly on the n-type epitaxial layer.

75. A transistor according to Claim 74, wherein the Schottky metal contact further comprises an overlayer on the first gate layer, wherein the overlayer comprises layers of platinum and gold.

76. A transistor according to Claim 75, wherein the Schottky metal contact is a mushroom gate.

77. A transistor according to Claim 76, further comprising a recess in the n-type epitaxial layer and wherein the first gate layer is formed in the recess in the n-type epitaxial layer.

78. A transistor according to Claim 76, wherein the mushroom gate is self aligned with respect to the recess.

79. A transistor according to Claim 60, further comprising:
a cap layer of n-type silicon carbide on the n-type epitaxial layer;
a recess in the cap layer;
a recess in the n-type epitaxial layer, wherein the recess in the n-type epitaxial
5 layer is within the recess in the cap layer; and
wherein the Schottky metal contact is within the recess in the n-type epitaxial layer.

80. A transistor according to Claim 79, wherein the recess in the n-type epitaxial layer extends to a depth of from about 20 nm to about 120 nm.

81. A transistor according to Claim 79, wherein the cap layer is doped at the same level as the n-type epitaxial layer.

82. A transistor according to Claim 79, wherein the cap layer has a dopant level from about $1 \times 10^{15} \text{ cm}^{-3}$ to about $5 \times 10^{17} \text{ cm}^{-3}$.

83. A transistor according to Claim 79, wherein the cap layer has a thickness of from about 50 nm to about 300 nm.

84. A transistor according to Claim 60 wherein the substrate comprises semi-insulating silicon carbide.

85. A transistor according to Claim 84, wherein the semi-insulating silicon carbide is substantially free of deep level dopants.

86. A transistor according to Claim 60, further comprising a contact to the p-type epitaxial layer.

87. A transistor according to Claim 86, further comprising:
a p⁺ well region formed in the p-type epitaxial layer; and
wherein the contact to the p-type epitaxial layer is formed on the p⁺ well region.

88. A transistor according to Claim 86, wherein the p-type epitaxial layer comprises:

a first p-type conductivity silicon carbide layer formed on the substrate; and
a second p-type conductivity silicon carbide layer formed on the substrate,
5 wherein the first p-type conductivity silicon carbide layer is more heavily doped than the second p-type conductivity silicon carbide layer.

89. A metal-semiconductor field-effect transistor comprising:
an n-type layer of n-type conductivity silicon carbide on a silicon carbide substrate;

ohmic contacts on the n-type layer and spaced apart that respectively define a
5 source and a drain; and

a region of chromium on the n-type layer that is between the ohmic contacts and thereby between the source and the drain so as to provide a Schottky metal contact to form an active channel in the n-type layer between the source and the drain when a bias is applied to the Schottky metal contact.

90. A transistor according to Claim 89, further comprising a p-type layer of p-type conductivity silicon carbide between the substrate and the n-type layer.

91. A transistor according to Claim 90, further comprising an ohmic contact formed on the p-type epitaxial layer.

92. A transistor according to Claim 91, further comprising a well region of p^+ silicon carbide formed in the p-type layer and wherein the ohmic contact is formed on the p^+ well region.

93. A transistor according to Claim 91, wherein the p-type layer comprises:

a first p-type epitaxial layer; and

5 a second p-type epitaxial layer, wherein the first p-type epitaxial layer has a doping concentration higher than a doping concentration of the second p-type epitaxial layer.

94. A transistor according to Claim 89, regions of n^+ silicon carbide between the n-type epitaxial layer and the ohmic contacts.

95. A transistor according to Claim 89 further comprising an overlayer on the ohmic contacts and the Schottky metal contact.

96. A transistor according to Claim 95, wherein the ohmic contacts comprise nickel and wherein the overlayer comprises layers of titanium, platinum and gold.

97. A transistor according to Claim 90, wherein the n-type and p-type layers forms a mesa having sidewalls extending from the n-type layer into the p-type layer which define the periphery of the transistor.

98. A transistor according to Claim 97 wherein the mesa further comprises the substrate and the sidewalls of the mesa extend into the substrate.

99. A transistor according to Claim 97, further comprising a passivation layer on the sidewalls of the mesa and exposed portions of the n-type epitaxial layer.

100. A transistor according to Claim 99, wherein the passivation layer is an ONO passivation layer.

101. A transistor according to Claim 89, further comprising metallization on the substrate opposite the n-type layer.

102. A transistor according to Claim 101, wherein the substrate has a thickness of 100 μm or less.

103. A transistor according to Claim 101, wherein the metallization comprises layers of titanium, platinum and gold coated with an overlayer of eutectic alloy of AuGe.

104. A transistor according to Claim 97, wherein the Schottky metal contact further comprises an overlayer on the chromium region, wherein the overlay comprises layers of platinum and gold.

105. A transistor according to Claim 89, wherein the Schottky metal contact is a mushroom gate.

106. A transistor according to Claim 89, further comprising a recess in the n-type layer and wherein the chromium region is in the recess in the n-type layer.

107. A transistor according to Claim 106, wherein the chromium region is self aligned.

108. A transistor according to Claim 89, wherein the ohmic contacts are directly on the n-type epitaxial layer.

109. A metal-semiconductor field-effect transistor comprising:
a bulk single crystal silicon carbide substrate;
an n-type epitaxial layer of n-type conductivity silicon carbide on the substrate;

5 ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain;

a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain to form an active

channel in the n-type epitaxial layer between the source and the drain when a bias is
10 applied to the Schottky metal contact;

wherein the n-type epitaxial layer forms a mesa having sidewalls extending
into the n-type layer which define the periphery of the transistor; and

an ONO passivation layer on the sidewalls of the mesa and exposed portions
of the n-type epitaxial layer.

110. A transistor according to Claim 109 wherein the mesa further
comprises the substrate and the sidewalls of the mesa extend into the substrate.

111. A transistor according to Claim 109, further comprising:

a p-type epitaxial layer of p-type conductivity silicon carbide between the
substrate and the n-type epitaxial layer; and

wherein the sidewalls of the mesa extends from the n-type layer into the p-
5 type layer.

112. A transistor according to Claim 111, further comprising an ohmic
contact formed on the p-type epitaxial layer.

113. A transistor according to Claim 112, further comprising a well region
of p⁺ silicon carbide formed in the p-type epitaxial layer and wherein the ohmic
contact is formed on the p⁺ well region.

114. A transistor according to Claim 112, wherein the p-type epitaxial layer
comprises:

a first p-type epitaxial layer; and

a second p-type epitaxial layer, wherein the first p-type epitaxial layer has a
5 doping concentration higher than a doping concentration of the second p-type
epitaxial layer.

115. A transistor according to Claim 109, wherein the ohmic contacts are
directly on the n-type epitaxial layer.

116. A transistor according to Claim 109, further comprising regions of n^+ silicon carbide between the n-type epitaxial layer and the ohmic contacts.
117. A transistor according to Claim 109, wherein the ohmic contacts comprise nickel contacts directly on the n-type epitaxial layer.
118. A transistor according to Claim 109 further comprising an overlayer on the ohmic contacts and the Schottky metal contact.
119. A transistor according to Claim 118, wherein the ohmic contacts comprise nickel and wherein the overlayer comprises layers of titanium, platinum and gold.
120. A transistor according to Claim 109, further comprising metallization formed on the substrate opposite the n-type layer.
121. A transistor according to Claim 120, wherein the substrate has a thickness of about 100 μm or less.
122. A transistor according to Claim 120, wherein the metallization comprises layers of titanium, platinum and gold coated with an overlayer of eutectic alloy of AuGe.
123. A transistor according to Claim 109, wherein the Schottky metal contact is a mushroom gate.
124. A transistor according to Claim 109, further comprising a recess in the n-type epitaxial layer and wherein the gate contact is formed in the recess in the n-type epitaxial layer.
125. A transistor according to Claim 124, wherein the gate contact is a self aligned gate contact.

126. A metal-semiconductor field-effect transistor comprising:
a semi-insulating silicon carbide substrate which is substantially free of deep
level dopants;
a buffer layer of silicon carbide on the semi-insulating silicon carbide
5 substrate;
an n-type epitaxial layer on the buffer layer;
a cap layer on the n-type epitaxial layer;
ohmic contacts on the n-type epitaxial layer that respectively define a source
and a drain;
10 a first recess in the cap layer between the source and drain contacts;
a second recess in the n-type epitaxial layer within the first recess;
a Schottky metal contact on the n-type epitaxial layer that is between the
ohmic contacts and thereby between the source and the drain to form an active
channel in the n-type epitaxial layer between the source and the drain when a bias is
15 applied to the Schottky metal contact, wherein the Schottky metal contact includes a
layer of chromium on the n-type epitaxial layer in the second recess;
wherein the n-type epitaxial layer forms a mesa having sidewalls extending
into the n-type layer which define the periphery of the transistor; and
an ONO passivation layer on the sidewalls of the mesa and exposed portions
20 of the n-type epitaxial layer.

127. A transistor according to Claim 126, wherein the buffer layer
comprises a p-type epitaxial layer of selectively doped p-type conductivity silicon
carbide between the substrate and the n-type epitaxial layer, wherein the p-type
conductivity silicon carbide has a carrier concentration of from about 1×10^{16} to about
5 $1 \times 10^{17} \text{ cm}^{-3}$.

128. A transistor according to Claim 126, wherein the buffer layer
comprises undoped silicon carbide.

129. A method of fabricating a passivation layer of a silicon carbide
semiconductor device, comprising:
forming an oxide layer on the silicon carbide semiconductor device; and then
annealing the oxide layer in a NO environment.

130. A method according to Claim 129, wherein the step of forming an oxide layer comprises the step of thermally growing an oxide layer.

131. A method according to Claim 129, wherein the step of forming an oxide layer comprises the step of depositing an oxide layer on the silicon carbide semiconductor device.

132. A method according to Claim 129, wherein the passivation layer is an ONO passivation layer, and wherein the annealing step is followed by the steps of:
depositing a layer of Si_3N_4 on the oxidized SiO_2 layer; then
oxidizing the layer of Si_3N_4 .

133. A method according to Claim 132, wherein the step of forming an oxide layer comprises the steps of:

high temperature annealing exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer in an H_2 ambient; then
5 forming an SiO_2 layer on the exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer; then
argon annealing the SiO_2 layer; then
oxidizing the SiO_2 layer.

134. A method of fabricating a metal-semiconductor field-effect transistor comprising:

forming a p-type epitaxial layer of selectively doped p-type conductivity silicon carbide on a single crystal silicon carbide substrate, wherein the p-type
5 conductivity silicon carbide has a carrier concentration of from about 1×10^{16} to about $1 \times 10^{17} \text{ cm}^{-3}$; then

forming an n-type epitaxial layer of n-type conductivity silicon carbide on the p-type epitaxial layer, wherein the n-type epitaxial forms a mesa having sidewalls extending into the n-type layer which define the periphery of the transistor;

10 forming ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain; and

forming a Schottky metal contact on the n-type epitaxial layer that is between the ohmic contacts and thereby between the source and the drain; and

forming an ONO passivation layer on the sidewalls of the mesa and exposed portions of the n-type epitaxial layer.

135. A method according to Claim 134 further comprising the step of etching the n-type epitaxial layer and the p-type epitaxial layer to form a mesa.

136. A method according to Claim 134, wherein the steps of forming ohmic contacts and forming a Schottky gate contact are preceded by the steps of:

etching the n-type epitaxial layer and the p-type epitaxial layer to form a mesa;

and

5 forming an ONO passivation layer on the exposed surfaces of the mesa.

137. A method according to Claim 136, wherein the step of forming an ONO passivation layer comprises the steps of:

high temperature annealing exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer in an H₂ ambient; then

5 forming an SiO₂ layer on the exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer; then

argon annealing the SiO₂ layer; then

oxidizing the SiO₂ layer; then

depositing a layer of Si₃N₄ on the oxidized SiO₂ layer; then

10 oxidizing the layer of Si₃N₄.

138. A method according to Claim 137, wherein the high temperature anneal is carried out at a temperature of greater than about 900 °C for a time of from about 15 minutes to about 2 hours.

139. A method according to Claim 137, wherein the argon anneal is carried out at a temperature of about 1200 °C for a time of about 1 hour.

140. A method according to Claim 137, wherein the step of forming an SiO₂ layer comprises the step of forming an SiO₂ layer to a thickness of from about 50 to about 500 Å.

141. A method according to Claim 137, wherein the step of forming an SiO₂ layer comprises forming an SiO₂ layer through a dry oxide process at a temperature of about 1200 °C.

142. A method according to Claim 137, wherein the step of oxidizing the SiO₂ layer comprises the step of oxidizing the SiO₂ layer in a wet environment at a temperature of about 950 °C for a time of about 180 minutes.

143. A method according to Claim 137, wherein the step of depositing a layer of Si₃N₄ comprises the step of depositing a layer of Si₃N₄ to a thickness of from about 200 to about 2000 Å.

143. A method according to Claim 137, wherein the step of depositing a layer of Si₃N₄ comprises the step of depositing a layer of Si₃N₄ through chemical vapor deposition.

144. A method according to Claim 137, wherein the step of oxidizing the layer of Si₃N₄ comprises the step of oxidizing the Si₃N₄ layer in a wet environment at a temperature of about 950 °C for a time of about 180 minutes.

145. A method according to Claim 137, wherein the step of oxidizing the layer of Si₃N₄ comprises the step of oxidizing the Si₃N₄ layer to provide an oxide layer having a thickness of from about 20 to about 200 Å.

146. A method according to Claim 137, wherein the step of depositing a layer of Si₃N₄ on the oxidized SiO₂ layer is preceded by the step of annealing the oxidized SiO₂ layer in a NO environment.

147. A method according to Claim 134, further comprising the step of forming a gate recess in the n-type epitaxial layer and wherein the step of forming a

Schottky gate contact comprises the step of forming a Schottky gate contact in the gate recess.

148. A method according to Claim 147, further comprising the step of:
etching through the ONO passivation layer and into the n-type epitaxial layer
so as to provide a gate recess in the n-type epitaxial layer; and
wherein the step of forming a Schottky gate contact comprises the step of
5 forming a Schottky gate contact in the gate recess utilizing the ONO passivation layer
as a mask.

149. A method according to Claim 148, wherein the step of etching through
the ONO passivation layer is followed by the step of patterning the ONO passivation
layer so as to provide a ledge in sidewalls of the opening of the ONO passivation
layer for the gate recess; and
5 wherein the step of forming a Schottky gate contact in the gate recess
comprises the step of forming a mushroom gate structure in the gate recess and on the
sidewalls and ledge of the ONO passivation layer.

150. A method according to Claim 148, wherein the step of etching through
the ONO passivation layer is carried out by at least one of Electron Cyclotron
Resonance and Inductively Coupled Plasma etching.

151. A method according to Claim 147, wherein the step of forming a gate
recess is preceded by the steps of:
forming a cap layer of silicon carbide on the n-type epitaxial layer;
etching through the cap layer to provide a first recess;
5 wherein the step of forming an ONO passivation layer comprises forming an
ONO passivation layer on the cap layer;
etching through the ONO passivation layer and into the n-type epitaxial layer
so as to provide a second recess in the n-type epitaxial layer, wherein the second
recess is within the first recess; and
10 wherein the step of forming a Schottky gate contact comprises the step of
forming a Schottky gate contact in the second recess utilizing the ONO passivation
layer as a mask.

152. A method according to Claim 134, further comprising the step of implanting n^+ well regions in the n-type epitaxial layer so as to provide source and drain regions and wherein the step of forming ohmic contacts comprises the step of forming ohmic contacts on the n^+ well regions.

153. A method according to Claim 134, further comprising the steps of:
thinning the substrate; and then
forming a metallization layer on the substrate opposite the p-type epitaxial layer.

154. A method according to Claim 153, wherein the step of forming a metallization layer comprises the steps of:
forming a titanium layer on the substrate opposite the p-type epitaxial layer;
then
5 forming a layer of platinum on the titanium layer; and then
forming a layer of gold on the layer of platinum.

155. A method according to Claim 153, further comprising the step of forming a layer of a eutectic alloy of AuGe on the layer of gold.

156. A method of fabricating a gate structure for a silicon carbide field effect transistor comprising the steps of:
forming an ONO passivation layer on exposed surfaces of a mesa terminated silicon carbide field effect transistor;
5 forming a gate window in the ONO passivation layer;
forming a gate recess in a channel layer of the mesa terminated silicon carbide transistor;
forming a gate contact in the gate recess in the channel layer.

157. A method according to Claim 156, wherein the step of forming an ONO passivation layer comprises the steps of:
high temperature annealing exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer in an H_2 ambient; then

- 5 forming an SiO₂ layer on the exposed portions of the substrate, p-type
 epitaxial layer and n-type epitaxial layer; then
 argon annealing the SiO₂ layer; then
 oxidizing the SiO₂ layer; then
 depositing a layer of Si₃N₄ on the oxidized SiO₂ layer; then
10 oxidizing the layer of Si₃N₄.

158. A method according to Claim 157, wherein the step of depositing a layer of Si₃N₄ on the oxidized SiO₂ layer is preceded by the step of annealing the oxidized SiO₂ layer in a NO environment.

159. A method according to Claim 157, wherein the high temperature anneal is carried out at a temperature of greater than about 900 °C for a time of from about 15 minutes to about 2 hours.

160. A method according to Claim 157, wherein the argon anneal is carried out at a temperature of about 1200 °C for a time of about 1 hour.

161. A method according to Claim 157, wherein the step of forming an SiO₂ layer comprises the step of forming an SiO₂ layer to a thickness of from about 50 to about 500 Å.

162. A method according to Claim 157, wherein the step of forming an SiO₂ layer comprises forming an SiO₂ layer through a dry oxide process at a temperature of about 1200 °C.

163. A method according to Claim 157, wherein the step of oxidizing the SiO₂ layer comprises the step of oxidizing the SiO₂ layer in a wet environment at a temperature of about 950 °C for a time of about 180 minutes.

164. A method according to Claim 157, wherein the step of depositing a layer of Si₃N₄ comprises the step of depositing a layer of Si₃N₄ to a thickness of from about 200 to about 2000 Å.

165. A method according to Claim 157, wherein the step of depositing a layer of Si_3N_4 comprises the step of depositing a layer of Si_3N_4 through chemical vapor deposition.

166. A method according to Claim 157, wherein the step of oxidizing the layer of Si_3N_4 comprises the step of oxidizing the Si_3N_4 layer in a wet environment at a temperature of about 950 °C for a time of about 180 minutes.

167. A method according to Claim 157, wherein the step of oxidizing the layer of Si_3N_4 comprises the step of oxidizing the Si_3N_4 layer to provide an oxide layer having a thickness of from about 20 to about 200 Å.

168. A method according to Claim 156, wherein the step of forming a gate contact comprises the step of forming a gate contact in the gate recess utilizing the ONO passivation layer as a mask.

169. A method according to Claim 168, further comprising the step of patterning the ONO passivation layer so as to provide a ledge in sidewalls of the opening of the ONO passivation layer for the gate recess; and

5 wherein the step of forming a gate contact in the gate recess comprises the step of forming a mushroom gate structure in the gate recess and on the sidewalls and ledge of the ONO passivation layer.

170. A method according to Claim 156, wherein the steps of forming a gate window and forming a gate recess are carried out by etching through the ONO passivation layer and into the channel layer by at least one of Electron Cyclotron Resonance and Inductively Coupled Plasma etching.

171. A method of forming a metal-semiconductor field-effect transistor, comprising:

forming an n-type epitaxial layer of n-type conductivity silicon carbide on a silicon carbide substrate;

5 forming ohmic contacts on the n-type epitaxial layer that respectively define a source and a drain;

- forming a cap layer of n-type silicon carbide on the n-type epitaxial layer;
forming a first recess in the cap layer;
forming a second recess in the n-type epitaxial layer, wherein the recess in the
10 n-type epitaxial layer is within the first recess in the cap layer; and
forming a Schottky metal contact on the n-type epitaxial layer that is between
the ohmic contacts and thereby between the source and the drain to form an active
channel in the n-type epitaxial layer between the source and the drain when a bias is
applied to the Schottky metal contact wherein the Schottky metal contact is within the
15 recess in the n-type epitaxial layer.

172. A method according to Claim 171, wherein the steps of forming an n-type epitaxial layer and forming a cap layer comprises the step of epitaxially growing the n-type epitaxial layer and the cap layer in a single growth step.

173. A method according to Claim 172, wherein an n-type dopant concentration in the single growth step is changed to grow the cap layer.

174. A method according to Claim 171, wherein the step of forming a first recess in the cap layer comprises the step of patterning the cap layer to form the first recess.

175. A method according to Claim 172, further comprising the steps of:
forming a mesa having sidewalls which extend through the cap layer and the
n-type epitaxial layer; and
wherein the step of patterning the cap layer to form the first recess is followed
5 by the steps of:
forming an ONO passivation layer on exposed surfaces of the mesa and the
first recess;
forming a gate window in the ONO passivation layer, wherein the gate
window is within the first recess;
10 forming the second recess in n-type epitaxial layer; and
forming a gate contact in the second recess.

176. A method according to Claim 175, wherein the step of forming an ONO passivation layer comprises the steps of:

high temperature annealing exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer in an H_2 ambient; then

5 forming an SiO_2 layer on the exposed portions of the substrate, p-type epitaxial layer and n-type epitaxial layer; then

argon annealing the SiO_2 layer; then

oxidizing the SiO_2 layer; then

depositing a layer of Si_3N_4 on the oxidized SiO_2 layer; and then

10 oxidizing the layer of Si_3N_4 .

177. A method according to Claim 176, wherein the step of depositing a layer of Si_3N_4 on the oxidized SiO_2 layer is preceded by the step of annealing the oxidized SiO_2 layer in a NO environment.

178. A method according to Claim 175, wherein the step of forming a gate contact comprises the step of forming a gate contact in the second recess utilizing the ONO passivation layer as a mask.

179. A method according to Claim 178, wherein the step of forming a gate contact in the second recess comprises the step of forming a mushroom gate structure in the second recess.

180. A method according to Claim 175, wherein the steps of forming a gate window and forming a second recess are carried out by etching through the ONO passivation layer and into the n-type epitaxial layer by at least one of Electron Cyclotron Resonance and Inductively Coupled Plasma etching.

181. A method according to Claim 171, wherein the step of forming a substrate comprises the step of forming a semi-insulating SiC substrate which is substantially free of deep-level dopants.

182. A method according to Claim 171, further comprising the step of forming a buffer layer between the substrate and the n-type epitaxial layer.

183. A method according to Claim 182, wherein the step of forming a buffer layer comprises the step of forming an undoped silicon carbide epitaxial layer.

184. A method according to Claim 182, wherein the step of forming a buffer layer comprises the step of forming an n-type silicon carbide epitaxial layer.

185. A method according to Claim 182, wherein the step of forming a buffer layer comprises the step of forming a p-type silicon carbide epitaxial layer.

186. A method according to Claim 183, wherein the step of forming a p-type epitaxial layer comprises the steps of:

forming a first p-type epitaxial layer on the substrate; and

forming a second p-type epitaxial layer on the first p-type epitaxial layer,

5 wherein the second p-type epitaxial layer has a lower dopant concentration than the first p-type epitaxial layer.

187. A method according to Claim 185, further comprising the step of forming an ohmic contact to the p-type epitaxial layer.

188. A method according to Claim 187, further comprising the step of implanting p-type dopants in the p-type epitaxial layer so as to provide a region of p-type conductivity silicon carbide having a higher carrier concentration than the p-type epitaxial layer; and

5 wherein the step of forming an ohmic contact comprises the step of forming an ohmic contact on the implanted region.

189. A method according to Claim 187, wherein the step of forming an ohmic contact comprises the steps of:

etching a ground contact window through the cap layer and the n-type epitaxial layer in a region adjacent a source region of the MESFET; and

forming the ohmic contact in the ground contact window.




Fig. 1




Fig. 2

2/10




Fig. 3A




Fig. 3B

3/10




Fig. 4




Fig. 5

4/10




Fig. 6A




Fig. 6B




Fig. 6C




Fig. 6D




Fig. 6E




Fig. 6F




Fig. 6G




Fig. 6H




Fig. 6I




FIG. 7




FIG. 8

8/10





Fig. 9



LABEL: DEVICE 533: $V_{dr} = 60.00V$
 $V_g = -8.00V$; STEP 57700

FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
15 November 2001 (15.11.2001)

PCT

(10) International Publication Number
WO 01/86727 A3

(51) International Patent Classification⁷: **H01L 29/24**

(21) International Application Number: PCT/US01/04957

(22) International Filing Date: 15 February 2001 (15.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/567,717 10 May 2000 (10.05.2000) US

(71) Applicant: **CREE, INC.** [US/US]; 4600 Silicon Drive,
Durham, NC 27703 (US).

(72) Inventors: **ALLEN, Scott, T.**; 1915 Misty Water Court,
Apex, NC 27502 (US). **PALMOUR, John, W.**; 2920
Hunter's Bluff Drive, Raleigh, NC 27606 (US). **AL-**
CORN, Terrence, S.; 300 Edgemore Avenue, Apex, NC
27502 (US).

(74) Agent: **MYERS, BIGEL, SIBLEY & SAJOVEC, P.A.**;
P.O. Box 37428, Raleigh, NC 27627 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).


Published:

— with international search report

(88) Date of publication of the international search report:
21 March 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **SILICON CARBIDE METAL-SEMICONDUCTOR FIELD EFFECT TRANSISTORS AND METHODS OF FABRICATING SILICON CARBIDE METAL-SEMICONDUCTOR FIELD EFFECT TRANSISTORS**



(57) Abstract: SiC MESFETs are disclosed which utilize a semi-insulating SiC substrate which substantially free of deep-level dopants. Utilization of the semi-insulating substrate may reduce back-gating effects in the MESFETs. Also provided are SiC MESFETs with a two recess gate structure. MESFETs with a selectively doped p-type buffer layer are also provided. Utilization of such a buffer layer may reduce output conductance by a factor of 3 and produce a 3db increase in power gain over SiC MESFETs with conventional p-type buffer layers. A ground contact may also be provided to the p-type buffer layer and the p-type buffer layer may be made of two p-type layers with the layer formed on the substrate having a higher dopant concentration. SiC MESFETs according to embodiments of the present invention may also utilize chromium as a Schottky gate material. Furthermore, an oxide-nitride-oxide (ONO) passivation layer may be utilized to reduce surface effects in SiC MESFETs. Also, source and drain ohmic contacts may be formed directly on the n-type channel layer, thus, the n+ regions need not be fabricated and the steps associated with such fabrication may be eliminated from the fabrication process. Methods of fabricating such SiC MESFETs and gate structures for SiC FETs as well as passivation layers are also disclosed.

WO 01/86727 A3

INTERNATIONAL SEARCH REPORT

 International Application No
 PCT/US01/04957

 A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 H01L29/24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

 Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, IBM-TDB

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 518 683 A (CREE RESEARCH INC) 16 December 1992 (1992-12-16)	1,10-13, 15-17, 19,27, 29, 60-65, 67-69, 71,84,85
Y	the whole document	2-4
Y	US 5 900 648 A (KONSTANTINOV ANDREI ET AL) 4 May 1999 (1999-05-04) column 5, line 16-42	2-4
A	US 5 229 625 A (UEMOTO ATSUKO ET AL) 20 July 1993 (1993-07-20) the whole document	1-4

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

10 December 2001

Date of mailing of the international search report

12.12.01

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Boetticher, H

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 01/04957

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☒ Claims Nos.: 28,30-32,33-59,86-88,89-108,109-128,134-155,156-170,171-189
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

As a result of the prior review under R. 40.2(e) PCT,
all additional fees are to be refunded.

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☒ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
1-4,10-13,15-17,19,27,29,60-65,67-69,71,84,85

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

☒ The additional search fees were accompanied by the applicant's protest.

☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 28,30-32,33-59,86-88,89-108,109-128,134-155,156-170,171-189

The number of 186 claims resulting in 26 pages of claims is excessive in view of 26 pages of description, so that the claims as a whole are not concise, contrary to the requirements of Article 6 PCT. The excessive number of claims covers a multitude of inventions not linked by a single general inventive concept in the sense of Rule 13.1 PCT, because of the disclosure of EP 0 518 683 A1 (same Applicant) found during search.

The Applicant has paid further search fees under protest. When starting further searches, it was found that the excessive number of claims results in further lack of unity: E.g. Cr Schottky contacts on SiC are known, so the features of claim 89 no longer form a single general inventive concept under Rule 13.1 PCT. Furthermore, inconsistencies in the claims were detected, e.g. in claims 109, 110, 111, a mesa is said to extend into an N-type layer, a substrate, a p-type layer, respectively, meaning three different embodiments which should have been claimed in independent claims.

Since all this results from the excessive number of claims, under Article 17(2)(a) PCT the International Searching Authority considers that the claims fail to comply with prescribed requirements and a meaningful search cannot be carried out.

The additional search fees paid under protest therefore had to be refunded.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-4,10-13,15-17,19,27,29; 60-65,67-69,71,84,85

A metal semiconductor field effect transistor comprising a semi-insulating silicon carbide substrate, an n-type layer on this substrate, ohmic contacts on this layer that respectively define a source and a drain, a Schottky metal contact on this layer that is between the ohmic contacts (claim 1).

A metal semiconductor field effect transistor further comprising a p-type layer between the n-type layer and the substrate (claim 60).

Both kinds of MESFETs are derivable from EP 0 518 683 A1.

2. Claims: 5-9; 79-83

An additional cap layer and recesses in the cap layer and the underlying layer.

3. Claim : 14; 66

Specific materials for ohmic contacts and overlayers.

4. Claim : 18; 70

An ONO passivation layer.

5. Claim : 20; 72

Specific substrate thickness.

6. Claim : 21; 73

Specific materials for metallization on substrate bottom.

7. Claims: 22-26; 74-78

Schottky contact material, shape and location.

8. Claim : 28

N-type buffer layer between substrate and n-type layer.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

9. Claims: 30-32; 86-88

Ohmic contact to p-type buffer layer.

10. Claims: 33-59

MESFET further having cap layer on n-type layer and recesses in these layers. (There may arise a further lack of unity if the features of independent claim 33 turn out to be known.)

11. Claims: 89-108

A MESFET having chromium for the Schottky gate on an n-type layer. Since Cr-SiC Schottky barriers are known there is a further lack of unity (for the resulting various inventions and any required extra fees see the remarks for extra fees made with respect to claims 29 to 32, 11, 13 to 26, and 10, for claims 90 to 93, 94, 95 to 107, and 108, respectively.)

12. Claims: 109-125

A MESFET having an ONO passivation layer on mesa sidewalls and on exposed portions of the n-type layer. Since the said EP 0 518 683 mentions that any known passivation may be used, with ONO being a known passivation, the features of claim 109 cannot form a common inventive concept causing a further lack of unity (for the resulting various inventions and any required extra fees see the remarks for extra fees made with respect to claims 16, 29 to 32, 10 to 14, 19 to 21, and 24 to 26 for claims 110, 111 to 114, 115 to 119, 120 to 122, and 123 to 125, respectively).

13. Claims: 126-128

MESFET with cap layer on n-type layer and respective recesses, and with ONO passivation layer.

14. Claims: 129-133

Method of fabricating a passivation layer.

15. Claims: 134-155

Method of forming MESFET with p-type layer between n-type layer and SiC substrate, with ONO passivation layer.

16. Claims: 156-170

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Method of fabricating a gate structure.

17. Claims: 171-189

Method of forming MESFET with cap layer on n-type layer and respective recesses in these layers.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US01/04957

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0518683	A	16-12-1992	US 5270554 A	14-12-1993
			EP 0518683 A1	16-12-1992
			JP 5175239 A	13-07-1993

US 5900648	A	04-05-1999	DE 69511726 D1	30-09-1999
			DE 69511726 T2	16-12-1999
			EP 0799499 A2	08-10-1997
			JP 10510952 T	20-10-1998
			WO 9619834 A2	27-06-1996

US 5229625	A	20-07-1993	JP 63047983 A	29-02-1988
			DE 3727019 A1	25-02-1988
			US 4897710 A	30-01-1990
